



**CORONADO**  
P A I N T

**SECTION NO. 2**  
**ADS – 313**  
**1160 Line**  
**Rev. 05/11**



**Super Kote™ 5000**  
**Acrylic Satin Enamel**  
**1160 Line**

<b>Type</b> Vinyl Acetate/Acrylic	<b>Sheen</b> Satin	<b>Theoretical Spread Rate</b> 350 – 450 Sq. Ft. Per Gallon*	<b>Recommended Application</b> Brush, Roller, Pad or Spray	<b>Thinner</b> Clean Water	<b>Clean Up</b> Warm Soapy Water
<b>Dry Time:</b>		<b>Tack Free:</b> 30 Minutes	<b>Recoat:</b> 4 Hours	<b>Full Cure:</b> 10 Days	

<b>PRODUCT NAME:</b> 1160 Line Super Kote 5000™ Acrylic Satin Enamel	Super Kote 5000™ Acrylic Satin Enamel is suited for wall and trim applications in kitchens, bathrooms, family rooms, hallways and children's bedrooms where routine cleaning is needed. Fast dry, low odor and a pleasant satin sheen make it an ideal finish for residential or commercial jobs.	
<b>WHERE TO USE:</b>	<b>Drywall Plaster Wood Metal Masonry Stucco</b>	Super Kote 5000™ Acrylic Satin Enamel can be applied to walls, woodwork, trim, paneling doors or dados. It is a good choice for interior bedrooms, family rooms, hallways, recreation rooms, commercial or rental properties. Also, may be used on exterior stucco, masonry and trim in southern climates where freezing temperatures are rare.

<b>REGULATORY INFORMATION:</b>	<b>VOC/VOS STATEMENT:</b>	<b>OTC CATEGORY:</b>	<b>MPI / LEED:</b>
	The products supported by this data sheet contain a maximum of 100 grams per liter VOC / VOS (0.83 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.	This product is certified under MPI #43. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.

<b>SURFACE PREPARATION:</b>	<p>Surface to be coated must be clean and free of dirt, chalk, wax, mildew, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Mildew must be removed by scrubbing with a solution of one part household bleach and three parts water. Rinse well with clean water and allow it to dry thoroughly before painting. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using CORONADO® Sur-Prep™ I Oil &amp; Grease Emulsifier. Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p><b>PRIMING (New or Bare Surfaces):</b>  <b>Plaster/Drywall</b> – Use CORONADO® Primer Sealer 40-11 or 78-11  <b>Wood</b> – Use CORONADO® Undercoat 37-11 or 78-11  <b>Smooth Masonry</b> – Use CORONADO® Masonry Sealer 48-11  <b>Block</b> – Use CORONADO® Block Filler 958-11  <b>Ferrous Metal</b> – Use CORONADO® Metal Primers 35-111, 35-147, 35-153 or 36-11  <b>Non-Ferrous Metal</b> – Use 116-11 Grip &amp; Seal™  <b>Galvanized</b> – Use 116-11 Grip &amp; Seal™</p>
-----------------------------	---

<b>APPLICATION:</b>	Stir thoroughly with a circular lifting motion before you begin to paint. Apply by brush, roller, pad or spray at a spread rate of up to 450 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results use a quality synthetic filament brush. For roller application use a ¼" or 3/8" nap cover for smooth surfaces, a ½" nap cover for semi-rough surfaces, and a ¾" nap cover for rough surfaces. For spray application, Acrylic Satin Enamel may be thinned with clean water up to 15% reduction if necessary.
<b>*NOTE ON SPREAD RATE:</b>	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.
<b>RESIN TYPE:</b>	Vinyl Acetate/Acrylic
<b>SOLIDS:</b>	Weight: 46.8 ± 1.0%      Volume: 32.8 ± 1.0%
<b>WEIGHT PER GALLON:</b>	10.6 lbs.
<b>VISCOSITY:</b>	90 - 95 KU (Krebs Units)
<b>FLASH POINT:</b>	200° F. or greater (TT-P-141, Method 4293)
<b>SPECULAR GLOSS:</b>	20 to 25 units @ 60 degrees
<b>SAG RATING:</b>	Pass 8 mils (Leneta)
<b>REC. FILM THICKNESS:</b>	Wet: 3.6 to 4.6 mils Dry: 1.2 to 1.5 mils
<b>LIGHT REFLECTANCE:</b>	92% (White or lightest colors)
<b>CAUTIONS:</b>	<p style="text-align: center;"><b>CAUTION!</b></p> <p style="text-align: center;"><b>Use only with adequate ventilation.</b></p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p><b>First Aid:</b> In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;"><b>Obtain and read the MSDS prior to using this product.</b> <b>KEEP OUT OF REACH OF CHILDREN</b></p>