



# CORONADO<sup>®</sup>

P A I N T

**SECTION NO. 7**  
**ADS – 800**  
**2 LINE**  
 Rev. 02/11

## Crylicote<sup>®</sup> Gold Collection Gloss 100% Acrylic House & Trim 2 Line

<b>Type</b> Acrylic	<b>Sheen</b> Gloss	<b>Theoretical Spread Rate</b> 325 - 425 Sq. Ft. Per Gallon*	<b>Recommended Application</b> Brush, Roller, Pad or Spray	<b>Thinner</b> Clean Water	<b>Clean Up</b> Warm Soapy Water
<b>Dry Time:</b>		<b>Tack Free:</b> 1 Hour	<b>Recoat:</b> 4 Hours	<b>Full Cure:</b> 7 – 10 Days	

<b>PRODUCT NAME:</b> 2 Line Crylicote <sup>®</sup> Gold Collection Gloss Acrylic House & Trim	Crylicote <sup>®</sup> Gold Acrylic House and Trim Enamel will provide a durable and protective finish on properly primed and prepared exterior surfaces. This Gloss Acrylic finish provides outstanding gloss and color retention.	
<b>WHERE TO USE:</b>	<b>Wood</b> <b>Metal</b> <b>Masonry</b> <b>Hardboard</b> <b>Vinyl</b>	On exterior fascia, siding, shutters and railings; an ideal gloss sheen for accenting trim work.

<b>REGULATORY INFORMATION:</b>	<b>VOC/VOS STATEMENT:</b>	<b>OTC CATEGORY:</b>	<b>MPI / LEED:</b>
	The products supported by this data sheet contain a maximum of 140 grams per liter VOC / VOS (1.17 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.	This product is not currently certified under MPI. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.

<b>SURFACE PREPARATION:</b>	<p>Surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with T.S.P. (or equivalent) and water, followed by a clean water rinse. Mildew must be removed by washing the surface with a solution of one part household bleach mixed with six parts water. Rinse well with clean water following wash. Wax should be removed by solvent cleaning. Grease should be cleaned by using CORONADO<sup>®</sup> Sur-Prep<sup>™</sup> I Oil &amp; Grease Emulsifier. Rust must be removed by hand scraping, feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p><b>Priming – (New or bare surfaces):</b>  <b>Wood</b> – Use CORONADO<sup>®</sup> Exterior Latex Primers 410-11, 8-11 or Exterior Alkyd Primers 9-11 or 5-11  <b>Ferrous Metal</b> – Use CORONADO<sup>®</sup> Metal Primers 35-111 or 36-11  <b>Non-Ferrous Metal</b> – Use CORONADO<sup>®</sup> Grip &amp; Seal Primer 116-11  <b>Galvanized</b> – Use CORONADO<sup>®</sup> Grip &amp; Seal Primer 116-11  <b>Masonry</b> – Use CORONADO<sup>®</sup> Masonry Sealer 48-11</p>
-----------------------------	--

<b>APPLICATION:</b>	Stir product with a circular, lifting motion before you begin to paint. Crylicote® Gold may be applied by brush, spray, pad or roller, at a rate of application not to exceed 425 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic bristle brush. For roller application, use a ¼" nap cover for smooth surfaces and a 3/8" or ½" nap cover for semi-rough surfaces. Thinning is not recommended, if necessary use water sparingly. For spray application, this product may be thinned up to 20% reduction if necessary. Avoid painting over hot surfaces or in direct sunlight. Apply when surface temperature is above 50° F. Do not apply if rain is threatening.	
<b>*NOTE ON SPREAD RATE:</b>	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.	
<b>RESIN TYPE:</b>	100% Acrylic	
<b>SOLIDS:</b>	Weight: 47.4 ± 1.0% Volume: 33.8 ± 1.0%	
<b>WEIGHT PER GALLON:</b>	10.5 lbs.	
<b>VISCOSITY:</b>	95 – 100 KU (Krebs Units)	
<b>FLASH POINT:</b>	200° F. or greater (TT-P-141, Method 4293)	
<b>SPECULAR GLOSS:</b>	45 – 55 units @ 60 Degrees	
<b>SAG RATING:</b>	Pass 8 mils (Leneta)	
<b>LIGHT REFLECTANCE:</b>	90% (White or Lightest Colors)	
<b>REC. FILM THICKNESS:</b>	Wet:	3.8 to 4.9 mils
	Dry:	1.3 to 1.7 mils
<b>QUALIFICATIONS:</b>	Meets the performance of MIL-P-28578	
<b>CAUTIONS:</b>	<p style="text-align: center;"><b>CAUTION!</b></p> <p style="text-align: center;"><b>Use only with adequate ventilation.</b></p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p><b>First Aid:</b> In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;"><b>Obtain and read the MSDS prior to using this product.</b> <b>KEEP OUT OF REACH OF CHILDREN</b></p>	