



CORONADO
P A I N T

SECTION NO. 2
ADS – 301
22 LINE
Rev. 11/11

Tough Walls™
100% Acrylic Semi - Gloss Enamel
22 Line

Type Acrylic	Sheen Semi – Gloss	Theoretical Spread Rate 350 – 450 Sq. Ft. Per Gallon*	Recommended Application Brush, Roller, Pad or Spray	Thinner Clean Water	Clean Up Warm Soapy Water
Dry Time:		Tack Free: 30 Minutes	Recoat: 4 Hours	Full Cure: 10 Days	

PRODUCT NAME: 22 Line Tough Walls™ 100% Acrylic Semi-Gloss Enamel	Tough Walls™ Semi-Gloss Enamel incorporates the latest in advanced acrylic formulating technology. The rich, semi-gloss finish is extremely stain resistant for easy cleaning maintenance. The spatter free formula applies beautifully and dries to a smooth, durable finish that can be scrubbed repeatedly without damaging the film. Tough Walls™ Semi-Gloss is a perfect choice for residential or commercial projects.	
WHERE TO USE:	Drywall Plaster Wood Metal Masonry Stucco	Tough Walls™ Semi-Gloss can be used on interior surfaces such as walls and woodwork in residential or commercial living and working spaces. Its durability lends itself to use in kitchens, bathrooms, laundries, family rooms, children's bedrooms, common areas, etc.

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 150 grams per liter VOC / VOS (1.25 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.	This product is not currently certified under MPI. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.

SURFACE PREPARATION:	<p>Surface to be painted must be clean and free of dirt, chalk, wax, mildew, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinse with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned off by using CORONADO® Sur-Prep™ I Oil & Grease Emulsifier, following all label directions. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Mildew must be removed by washing with a solution of 1 part household bleach and six parts water. Rinse thoroughly and allow it to dry. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be primed with the appropriate primer.</p> <p>PRIMING (New or Bare Surfaces): Plaster/Drywall – Use 40-11 Latex Primer Sealer or 78-11 Latex Undercoater Wood – Use 78-11 Latex Undercoater Masonry – Use 48-11 Masonry Sealer Ferrous Metal – Use 36-11 Latex Metal Primer Non-Ferrous Metal – Use 116-11 Grip & Seal™ Galvanized – Use 116-11 Grip & Seal™</p>
-----------------------------	--

APPLICATION:	<p>Stir product with a circular, lifting motion before beginning to paint. Tough Walls™ Semi-Gloss may be applied by brush, roller, pad or sprayer at a rate of application not to exceed 450 square feet per gallon. Surface texture and porosity will affect actual yield. For brush application, use a quality applicator with a synthetic filament. When applying on smooth surfaces, use a ¼" – 3/16" mohair type roller cover. On semi-rough and rough surfaces use a 3/8" - ¼" cover depending on the surface texture. For spray application, Tough Walls™ Semi-Gloss may be thinned with clean water as necessary, up to 10%. Thinning is not normally necessary for brush or roller application. Clean up with warm soapy water before the paint dries. Do not apply if surface or air temperatures are below 50° F.</p> <p>NOTE: Tough Walls™ Latex Semi-Gloss Enamel is suitable for use on exterior trim in southern climates where the temperatures never drop below 30° F; however, do not use on siding.</p>
*NOTE ON SPREAD RATE:	<p>Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.</p>
RESIN TYPE:	Acrylic
SOLIDS:	Weight: 46.0 ± 1.0% Volume: 32.0 ± 1.0%
WEIGHT PER GALLON:	10.5 lbs.
VISCOSITY:	95 – 100 KU (Krebs Units)
FLASH POINT:	200° F. or greater (TT-P-141, Method 4293)
SPECULAR GLOSS:	45 – 55 units @ 60 degrees
SAG RATING:	Pass 8 mils (Leneta)
REC. FILM THICKNESS:	Wet: 3.6 to 4.6 mils
	Dry: 1.1 to 1.5 mils
QUALIFICATIONS:	Meets the performance requirements of TT-P-1511, Type I
CAUTIONS:	<p style="text-align: center;">CAUTION!</p> <p style="text-align: center;">Use only with adequate ventilation.</p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p>First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN</p> <p style="text-align: center;">KEEP FROM FREEZING</p>