



CORONADO
P A I N T

SECTION NO. 1
ADS -201
24 LINE
Rev. 06/11



Tough Walls™
Latex Flat Enamel
24 Line

Type Acrylic	Sheen Low Sheen Flat	Theoretical Spread Rate 350 – 450 Sq. Ft. Per Gallon*	Recommended Application Brush, Roller, Pad or Airless Spray	Thinner Clean Water	Clean Up Warm Soapy Water
Dry Time:		Tack Free: 30 Minutes	Recoat: 4 Hours	Full Cure: 10 Days	

PRODUCT NAME: 24 Line Tough Walls™ Latex Flat Enamel	While Tough Walls™ appears a rich flat, when viewed at an angle a hint of soft luster can be detected. This subtle velvet sheen is what gives Tough Walls™ its extreme stain resistance, its washability and rich appearance. Plus Tough Walls™ applies easily, has excellent hiding power and dries quickly. Incorporating advanced acrylic resin technology and available in over 1,000 colors, Tough Walls™ is a perfect choice for residential or commercial projects.	
WHERE TO USE:	Drywall Plaster Wood Metal Cement Block Stucco	This low sheen flat enamel is an ideal finish for coating interior wall and trim surfaces where excellent durability is needed. It may be used for children's bedrooms and play areas, laundry rooms, dining rooms, bathrooms, hallways, commercial office spaces, etc.

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 50 grams per liter VOC / VOS (0.41 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Flat Coating.	This product is not currently certified under MPI. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a flat coating.

SURFACE PREPARATION:	<p>The surface to be painted must be clean and free of dirt, chalk, wax, grease, rust, flaking paint or any other surface contamination that could affect product performance. Dirt and chalk should be removed by scrubbing with warm, soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning to SSPC-SP 1. Grease and oil residue should be cleaned by using Coronado® Sur-Prep™ I Emulsifier. Follow all label directions. Rust must be removed by hand scraping vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Gloss surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>PRIMING (New or Bare Surfaces): Plaster/Drywall – For best results use Latex Primer Sealer 40-11 Wood – For best results use Latex Undercoat 78-11 Ferrous Metal – Use Latex Metal Primer 36-11 or Corotech V110 Galvanized Metal – Use Grip & Seal™ 116-11 Masonry – Use Masonry Sealer 48-11</p>
-----------------------------	---

APPLICATION:	<p>Stir product thoroughly with a circular, lifting motion before you begin to paint. Tough Walls™ may be applied by brush, roller, or spray at up to 450 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results use quality polyester or nylon filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 3/4" nap cover for semi-rough surfaces and up to a 1 1/2" nap cover for rough surfaces. For spray application, Tough Walls™ may be thinned up to 15% with clean water. Apply when surface and air temperatures are above 50° F.</p> <p>IMPORTANT: Examine the contents for proper color, as we cannot be responsible for incorrect color after application. Boxing or inter-mixing containers of different batch numbers on the same job is highly recommended. Apply product as it comes in the can. The addition of paint additives is not recommended.</p>
*NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.
RESIN TYPE:	Acrylic Polymer
SOLIDS:	Weight: 52.6 ± 1.0% Volume: 34.8 ± 1.0%
WEIGHT PER GALLON:	11.6 lbs.
VISCOSITY:	100 - 106 KU (Krebs Units)
FLASH POINT:	200° F. or greater (TT-P-141, Method 4293)
SPECULAR GLOSS:	7 – 10 units @ 85 Degrees
SAG RATING:	Pass 8 mils (Leneta)
REC. FILM THICKNESS:	Wet: 3.6 to 4.6 mils Dry: 1.3 to 1.7 mils
LIGHT REFLECTANCE:	89% (White)
QUALIFICATIONS:	Meets the performance requirements of TT-P-29.
CAUTIONS:	<p style="text-align: center;">CAUTION!</p> <p style="text-align: center;">Use only with adequate ventilation.</p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p>First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN</p> <p style="text-align: center;">KEEP FROM FREEZING</p>