



Gold Acrylic Latex Flat 26 Line

Type	Sheen	Theoretical Spread Rate	Recommended Application	Thinner	Clean Up
Acrylic	Flat	300 to 400 Sq. Ft. Per Gallon*	Brush, Roller Pad or Airless Spray	Clean Water	Warm Soapy Water
Dry Time:		Tack Free: 30 Minutes	Recoat: 4 Hours	Full Cure: 10 Days	

PRODUCT NAME: 26 Line Gold Acrylic Latex Flat	Gold Acrylic Latex Flat dries to a very flat finish, which lends itself to excellent touch-up. This product exhibits outstanding hiding and will cover most colors in one coat. This line is fully tintable and can be made into thousands of colors. The spatter resistant formula ensures easy, mess-free application for professionals and do-it-yourselfers alike. The durable acrylic film resists stains and repeated washings, and is excellent for use in high traffic areas.		
WHERE TO USE:	Drywall Plaster Wood Metal Cement Block	May be applied to interior surfaces where a fashionable flat finish is desirable, such as bedrooms, living rooms, dining rooms or hallways. Excellent for commercial or residential work.	

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 80 grams per liter VOC / VOS (0.67 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Flat Coating.	This product is certified under MPI #53. This product does not meet qualifications for LEED (Leadership in Energy and Environmental Design) projects.

SURFACE PREPARATION:	<p>New Work: The surface to be coated must be clean and free from dust, grease, wax, rust, oil, bleeding stains, or any other contaminate that could compromise product performance.</p> <p>Priming: Drywall – Self priming, but for best results use 40-11 Latex Primer Sealer Plaster – Self priming, but for best results use 40-11 Latex Primer Sealer Wood – Alkyd Primer Undercoat 37-11 or Latex Enamel Undercoat 78-11 Ferrous Metal – Rust Inhibiting Metal Primer 36-11 Non-Ferrous Metal – Perma Bond 100-10 or Grip & Seal™ 116-11. Galvanized – Perma Bond 100-10 or Grip & Seal™ 116-11. Masonry – Acrylic Masonry Sealer 48 Line.</p> <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces, remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust prior to recoating. Any loose or flaking paint should be removed and the edges feather sanded to produce a uniform surface.</p>
APPLICATION:	Stir product thoroughly with a circular, lifting motion evenly mix all ingredients. Apply evenly using the listed applicators. Avoid overworking or over spreading the product. Roller – 3/8" to 1 1/2" nap, depending on surface texture Brush – Nylon or polyester filament Airless Spray – Tip size at atomization pressure will vary with type of equipment, viscosity and temperature. A tip size of .X17 – .X19 will provide the most satisfactory spray pattern. Best results are most likely obtained using quality application tools. Do not apply directly over chalky surfaces or bleeding stains. Do not apply when temperatures are below 50° or above 95° F or if humidity is greater than 85%.

SECTION NO. 1
ADS-202
26 LINE

* NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.	
SOLIDS:	Weight: 55.2 ± 1.0%	Volume: 36.4 ± 1.0%
RESIN TYPE:	Acrylic	
COLORS / TINTING:	Gold Acrylic Latex Flat is available in White, Pastel Base and Tint Base. The bases can be shaded with universal (glycol based) colorants.	
WEIGHT PER GALLON:	11.9 lbs.	
VISCOSITY:	105 – 108 KU (Krebs Units)	
FLASH POINT:	200°F. or greater (TT-P-141, Method 4293)	
SPECULAR GLOSS:	0 - 4 units @ 85 degrees	
SAG RATING:	Pass 8 mils (Leneta)	
REC. FILM THICKNESS:	Wet:	4.0 to 5.3 mils
	Dry:	1.5 to 1.9 mils
LIGHT REFLECTANCE:	89% (White or lightest colors)	
QUALIFICATIONS:	Meets the performance specifications for TT-P-55, TT-P-29	
CAUTIONS:	<p style="text-align: center;">WARNING!</p> <p style="text-align: center;">OVEREXPOSURE MAY CAUSE KIDNEY DAMAGE. Contains: Ethylene Glycol. Causes eye irritation.</p> <p>Use only with adequate ventilation. Avoid breathing dust, vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes. Wash thoroughly after handling.</p> <p>First Aid: In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Get medical attention immediately. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting. Call physician immediately. If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p>WARNING: This product contains a chemical known to the state of California to cause cancer, birth defects or other reproductive harm.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product. KEEP OUT OF REACH OF CHILDREN</p>	