



CORONADO[®]

P A I N T

SECTION NO. 7
ADS – 807
410 Line
Rev. 08/11

Crylicote[®] Gold Collection Satin 100% Acrylic House & Trim 410 Line

Type	Sheen	Theoretical Spread Rate	Recommended Application	Thinner	Clean Up
Acrylic	Satin	350 – 450 Sq. Ft. Per Gallon*	Brush, Pad, Roller or Spray	Clean Water	Warm Soapy Water
Dry Time:		Tack Free: 30 Minutes	Recoat: 4 Hours	Full Cure: 7 – 10 Days	

PRODUCT NAME: 410 Line Crylicote [®] Gold Collection Satin 100% Acrylic House & Trim	Crylicote [®] Satin Exterior Latex House Paint provides tenacious adhesion to a variety of substrates. It is mildew and blister resistant, exhibits excellent durability and superb color retention. Crylicote [®] is famous as the paint that conquered Southern Yellow Pine. It is an excellent choice for painting pre-finished siding.	
WHERE TO USE:	Wood Metal Masonry Aluminum	Exterior – Virtually any exterior building surface will be suitable for Crylicote [®] . It is designed as a self-priming system on non-bleeding woods, masonry or clean and rust free galvanized surfaces. May also be applied over primed ferrous metal and aluminum.

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 100 grams per liter VOC / VOS (0.83 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.	This product is not currently certified under MPI. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.

SURFACE PREPARATION:	<p>The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by power washing or hand scrubbing with TSP (or equivalent) and water, followed by a clean water rinse. Mildew must be removed by washing the surface with a solution of one part household bleach mixed with three parts water. Rinse well with clean water following wash. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using CORONADO[®] Sur-Prep[™] I Oil & Grease Emulsifier. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. It is not necessary to dull glossy surfaces before painting as long as they are otherwise lean and free from contamination. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>Priming –(new or bare surfaces): Wood – Non-bleeding, such as Southern Yellow Pine, Ponderosa Pine, seal all knots with CORONADO[®] Seal-It[™] and spot prime nail heads with an exterior oil primer. Use two or three coats of Crylicote[®]. Redwood, Cedar or other bleeding type woods should be primed with CORONADO[®] Exterior Oil Primer, then top-coated with one or two coats of Crylicote. Galvanized – Crylicote[®] is self-priming. Apply two coats. Aluminum Siding – Crylicote[®] is self-priming. Apply two coats. Ferrous Metal – Use CORONADO[®] Primer 35-111, 36-11 Masonry – Crylicote[®] is self-priming. Apply two coats.</p>
-----------------------------	---

APPLICATION:	<p>Stir product with a circular, lifting motion before you begin to paint. Crylicote® may be applied by brush, spray, pad or roller at a rate of application not to exceed 450 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" or 1/2" nap cover for smooth surfaces, a 3/4" nap cover for semi-rough surfaces and a 1" or 1 1/2" nap cover for rough surfaces. For spray application, Crylicote® may be thinned with clean water, up to 20% reduction if necessary. Apply only when surface and air temperatures are between 50° F and 90° F. Do not apply if rain is threatening.</p> <p>May be applied with airless spray equipment. Tip sizes and atomization pressures will vary with the type of equipment used. Usually an 8 to 12 inch fan at one foot distance is ideal for airless and can be obtained with a tip size from .015 to .019 inches. Follow spray equipment manufacturers recommendations. Do not apply at more than recommended spread rate given on product label.</p>
*NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.
RESIN TYPE:	100% Acrylic
SOLIDS:	Weight: 52.5 ± 1.0% Volume: 38.3 ± 1.0%
WEIGHT PER GALLON:	10.8 lbs.
VISCOSITY:	95 – 100 (Krebs Units)
FLASH POINT:	200° F. (TT-P-141, Method 4293)
SPECULAR GLOSS:	32 – 37 units @ 85 Degrees
LIGHT REFLECTANCE:	89% (White or lightest colors)
SAG RATING:	Pass 8 mils (Leneta)
REC. FILM THICKNESS:	Wet: 3.6 to 4.6 mils Dry: 1.4 to 1.8 mils
CAUTIONS:	<p style="text-align: center;">WARNING!</p> <p style="text-align: center;">OVEREXPOSURE MAY CAUSE KIDNEY DAMAGE. HARMFUL OR FATAL IF SWALLOWED. Causes eye irritation. Contains Ethylene Glycol & Crystalline Silica</p> <p>Use only with adequate ventilation. Avoid breathing dust, vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes. Wash thoroughly after handling.</p> <p>First Aid: In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Get medical attention immediately. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting. Get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p>WARNING: This product contains chemicals known to the state of California to cause cancer, birth defects or other reproductive harm.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product. KEEP OUT OF REACH OF CHILDREN</p>