



CORONADO
P A I N T

SECTION NO. 2
ADS – 324
414 Line
Rev. 09/11

Super Kote 5000™ Acrylic High Gloss Enamel
414 Line

Type Acrylic	Sheen Gloss	Theoretical Spread Rate 350 - 450 Sq. Ft. Per Gallon*	Recommended Application Brush, Roller or Spray	Thinner Clean Water	Clean Up Warm Soapy Water
Dry Time:		Tack Free: 30 Minutes	Recoat: 2 Hours	Full Cure: 7-10 Days	

PRODUCT NAME: 414 Line Super Kote 5000™ Acrylic High Gloss Enamel	Super Kote 5000™ Acrylic High Gloss Enamel is an interior-exterior finish, which is suitable for coating primed wood, metal, drywall or masonry surfaces. It is water thinned so it poses no fire hazard or objectionable odor. Supreme High Gloss Enamel flows easily and dries quickly. The cured film exhibits excellent gloss and color retention and is resistant to water.	
WHERE TO USE:	Metal Wood Masonry Drywall	Designed for interior or exterior use in both residential and commercial applications. Suitable for coating walls, woodwork, furniture, ducts, gutters, metal buildings, shutters, cabinets, etc., or wherever beauty and easy maintenance is desired. Not recommended for unprimed wood or metal, for immersion service or in highly corrosive environments. Not to be used as house paint on wood siding.

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 140 grams per liter VOC / VOS (1.17 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Non-Flat High Gloss Coating.	This product is certified under MPI #114. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a Non-Flat Coating.

SURFACE PREPARATION:	<p>New Work: The surface to be coated must be clean and free of oil, grease, rust and other contamination that could interfere with adhesion.</p> <p>Priming – (New or Bare Surfaces): Ferrous Metal – Use CORONADO® Primers 180-11, 35-111, 35-147, 35-153 or 36-11 Non-Ferrous Metal – Use Perma Bond 100-10 Galvanized – Use Perma Bond 100-10, 180-11 or 36-11 Wood Interior – Use CORONADO® Undercoat 78-11 or Alkyd Undercoat 37-11 Wood Exterior – Use CORONADO® Primer 410-11 Drywall/Plaster – Use CORONADO® Primer/Sealer 40-11 or Grip & Seal™ 116-11 Concrete – Self Priming or Block Filler 958-11 or Masonry Sealer 48-11</p> <p>Repaint: The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Mildew must be removed by washing with a solution of 1 part household bleach and 3 parts water. Rinse well and allow it to dry. Wax should be removed by solvent cleaning. Grease should be cleaned by using CORONADO® Sur-Prep™ I. Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer as indicated under "New Work" above.</p>
-----------------------------	--

SECTION NO. 2
ADS-324
414 Line

APPLICATION:	<p>Stir Super Kote 5000™ Acrylic High Gloss Enamel thoroughly with a circular, lifting motion to assure even pigment dispersion. Super Kote 5000™ Acrylic High Gloss Enamel may be applied by brush, roller or spray.</p> <p>Roller – Use a 3/16" to 1/4" nap enameling cover for smooth surfaces, a 3/8" nap cover for semi-rough surfaces.</p> <p>Brush – Use a polyester or nylon filament brush</p> <p>Spray – May be sprayed using conventional or airless equipment. Can be thinned with clean water, up to 15% for spraying.</p> <p>For best results use quality applicator tools. Apply only when surface and air temperatures are between 50° F and 90° F.</p>
*NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.
RESIN TYPE:	Acrylic
COLORS / TINTING:	Available in white only. It can be tinted with up to 2 oz per gallon of universal (glycol-based) colorant.
SOLIDS:	Weight: 46.4 ± 1.0% Volume: 34.9 ± 1.0%
WEIGHT PER GALLON:	10.1 lbs.
VISCOSITY:	90 – 95 KU (Krebs Units)
FLASH POINT:	200° F. or greater (TT-P-141, Method 4293)
SPECULAR GLOSS:	70+ units @ 60 degrees
SAG RATING:	Pass 6 mils (Leneta)
REC. FILM THICKNESS:	Wet: 3.6 to 4.6 mils Dry: 1.2 to 1.6 mils
LIGHT REFLECTANCE:	90 (White)
CAUTIONS:	<p>CAUTION!</p> <p>Use only with adequate ventilation.</p> <p>Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p>First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p>Obtain and read the MSDS prior to using this product. KEEP OUT OF REACH OF CHILDREN</p>