



**ELASTITE™**  
**100% Acrylic Masonry Sealer – White**  
**48-11**

Type	Sheen	Theoretical Spread Rate	Recommended Application	Thinner	Clean Up
Acrylic	Flat	200 to 400 Sq. Ft. Per Gallon*	Brush, Roller or Spray	Clean Water	Warm Soapy Water
<b>Dry Time:</b>		<b>Tack Free:</b> 1 Hour	<b>Recoat:</b> 6 - 8 Hours	<b>Full Cure:</b> 7 - 10 Days	

<b>PRODUCT NAME:</b> 48-11 Elastite™ Acrylic Masonry Sealer - White	Elastite™ Acrylic Masonry Sealer is designed to penetrate deeply into the pores of masonry surfaces to stop dusting and to form a foundation to support the Elastite™ Coating System. An excellent chalk binding sealer resistant to the effects of alkali up to a pH of 13. This VOC compliant product is environmentally friendly.	
<b>WHERE TO USE:</b>	<b>Stucco</b> <b>Block</b> <b>Brick</b> <b>Concrete</b>	On new or bare stucco, block, brick, pre-cast concrete, poured in place concrete, fluted brick or stone surfaces. May be used on vertical or horizontal surfaces.
<b>SURFACE PREPARATION:</b>	The surface to be sealed must be dry, clean and free of dirt, oil, dust, mildew, form oil, release agents, rust or other surface contamination that could interfere with adhesion or penetration. For recoat work, any flaking paint or excessive chalk should be removed by thoroughly washing with a high pressure water blast. <b>NOTE:</b> New masonry must be allowed to age for a minimum of 7 days before sealing.	
<b>APPLICATION:</b>	Elastite™ Acrylic Masonry Sealer may be applied by brush, roller or spray at the recommended spread rate per gallon. Surface texture and application technique will dictate actual yield. Stir product thoroughly before use and occasionally during application. May be thinned with one half pint of water per gallon for additional penetration. Best rolling results are obtained with a 3/8" to 1" nap roller cover. When brushing or rolling, flow material on with a minimum of strokes. Allow 6 to 8 hours dry time before finish coat. <b>IMPORTANT:</b> Do not apply if rain is threatening. Do not apply if air or surface temperature is below 50° F or above 95° F.	
<b>*NOTE ON SPREAD RATE:</b>	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.	
<b>RESIN TYPE:</b>	Acrylic	
<b>SOLIDS:</b>	Weight: 46.2 ± 1.0% Volume: 33.3 ± 1.0%	
<b>WEIGHT PER GALLON:</b>	10.2 lbs	
<b>VISCOSITY:</b>	75 - 80 KU (Krebs Units)	
<b>FLASH POINT:</b>	200° F. or greater (TT-P-141, Method 4293)	
<b>SPECULAR GLOSS:</b>	0 – 8 units @ 60 Degrees	
<b>SAG RATING:</b>	Pass 6 mils (Leneta)	
<b>REC. FILM THICKNESS:</b>	Wet:	4.0 to 8.0 mils
	Dry:	1.3 to 2.7 mils
<b>LIGHT REFLECTANCE:</b>	89%	

<b>CAUTIONS:</b>	<p style="text-align: center;"><b>WARNING!</b></p> <p>VAPOR HARMFUL. CAUSES EYE AND SKIN IRRITATION. MAY BE HARMFUL IF ABSORBED THROUGH SKIN. HARMFUL IF SWALLOWED.</p> <p><b>Contains</b> Ethylene Glycol m-Butyl Ether. Vapor harmful. May affect the brain or nervous system causing dizziness, headache and nausea. Causes nose and throat irritation. Harmful if swallowed.</p> <p><b>NOTICE:</b> Reports have associated repeated and prolonged occupational overexposure to solvent with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. Contains Ethylene Glycol m-Butyl Ether which may cause blood damage based on animal data.</p> <p>Keep away from heat and flame. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation.</p> <p><b>Use only with adequate ventilation.</b> Do not breathe dust, vapors or spray mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling.</p> <p><b>First Aid:</b> In case of contact, immediately flush eyes or skin with plenty of water for at least 15 minutes. Remove contaminated clothing and shoes. Get medical attention immediately. Wash clothing before reuse. Thoroughly clean contaminated shoes. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. If swallowed, do not induce vomiting. Get medical attention immediately.</p> <p>If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;"><b>Obtain and read the MSDS prior to using this product.</b> <b>KEEP OUT OF REACH OF CHILDREN</b></p>
<b>VOC/VOS STATEMENT:</b>	This product contains a maximum of 200 grams VOC/VOS per liter of coating. (1.6 pounds per gallon)
<b>OTC CATEGORY:</b>	This product is compliant under the Ozone Transport Commission regulations as a Primer/Sealer/Undercoater in all container sizes.

05/09