



CORONADO
P A I N T

SECTION NO.2
ADS – 315
930 Line
Rev. 06/11



Super Kote 3000™
Vinyl Acrylic Eggshell Enamel
930 Line

Type Latex	Sheen Eggshell	Theoretical Spread Rate 300 - 400 Sq. Ft. Per Gallon*	Recommended Application Brush, Roller, Pad or Spray	Thinner Clean Water	Clean Up Warm Soapy Water
Dry Time:		Tack Free: 30 Minutes	Recoat: 4 Hours	Full Cure: 10 Days	

PRODUCT NAME: 930 Line Super Kote 3000™ Vinyl Acrylic Eggshell Enamel	Super Kote 3000™ Vinyl Acrylic Eggshell Enamel is designed particularly for the professional contractor. The formulation provides that necessary balance between performance and value. Super Kote 3000™ Vinyl Acrylic Eggshell Enamel demonstrates good hide and will withstand repeated washing without damaging the film. May be used for new work or re-do, commercial or residential applications.	
WHERE TO USE:	Drywall Plaster Wood Metal Masonry Stucco	Super Kote 3000™ Vinyl Acrylic Eggshell Enamel can be applied to walls, woodwork, trim, paneling, doors or dados. It is a good choice for interior bedrooms, family rooms, hallways, recreation rooms, commercial or residential properties.

REGULATORY INFORMATION:	VOC/VOS STATEMENT:	OTC CATEGORY:	MPI / LEED:
	The products supported by this data sheet contain a maximum of 50 grams per liter VOC / VOS (0.41 lbs/gal.) excluding water & exempt solvents.	This product is compliant under the Ozone Transport Commission regulations as a Non-Flat Coating.	This product is certified under MPI #44. This product does meet qualifications for LEED (Leadership in Energy and Environmental Design) projects as a non-flat coating.

SURFACE PREPARATION:	<p>Surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Mildew must be removed by scrubbing with a solution of one part household bleach and three parts water. Rinse well with clean water and allow it to dry thoroughly before painting. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using CORONADO® Sur-Prep™ I Oil & Grease Emulsifier. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>PRIMING – (New or Bare Surfaces): Plaster/Drywall – For best results use CORONADO® Primer Sealer 40-11 or 948-11. However, two un-thinned coats of Super Kote 3000™ Vinyl Acrylic Eggshell Enamel will provide satisfactory results. Wood – Use CORONADO® Undercoat 37-11 or 78-11 Smooth Masonry – Use CORONADO® Masonry Sealer 48-1 Block – Use CORONADO® Block Filler 958-11 Ferrous Metal – Use CORONADO® Metal Primers 35-111, 35-147, 35-153 or 36-11 Non-Ferrous Metal – Use Grip & Seal™ 116-11 Galvanized – Use Grip & Seal™ 116-11</p>
-----------------------------	--

APPLICATION:	Stir product with a circular, lifting motion before you begin to paint. Super Kote 3000™ Vinyl Acrylic Eggshell Enamel may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application use a ¼" or 3/8" nap cover for smooth surfaces, a ½" nap cover for semi-rough surfaces, and a ¾" nap cover for rough surfaces. May be reduced with clean water up to 15% for spray application. Do not jeopardize the success of your painting project by using poor quality applicator tools. Apply only when surface and air temperatures are between 50° F and 90° F.	
*NOTE ON SPREAD RATE:	Actual spread rate will vary based upon numerous factors, including texture of the substrate, application method, waste, surface porosity and thinning. The Theoretical Spread Rate listed on this document has not taken into account these factors and is only based upon the volume solids of this product and the recommended wet film thickness when applied to a smooth substrate.	
RESIN TYPE:	Vinyl Acrylic	
SOLIDS:	Weight: 45.6 ± 1.0%	Volume: 29.2 ± 1.0%
WEIGHT PER GALLON:	10.8 lbs.	
VISCOSITY:	92 – 97 KU (Krebs Units)	
FLASH POINT:	200°F. or greater (TT-P-141, Method 4293)	
SPECULAR GLOSS:	15-20 units @ 85 degrees	
SAG RATING:	Pass 6 mils (Leneta)	
REC. FILM THICKNESS:	Wet:	4.0 to 5.3 mils
	Dry:	1.2 to 1.6 mils
QUALIFICATIONS:	Certified under MPI #44.	
CAUTIONS:	<p style="text-align: center;">CAUTION!</p> <p style="text-align: center;">Use only with adequate ventilation.</p> <p style="text-align: center;">Ensure fresh air during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow manufacturer's directions for respirator use.</p> <p>First Aid: In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced get medical attention immediately. If swallowed, get medical attention immediately.</p> <p style="text-align: center;">If spilled, contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.</p> <p style="text-align: center;">Obtain and read the MSDS prior to using this product. KEEP OUT OF REACH OF CHILDREN</p>	