

**1C.201****DURALAQ™ PRO N/C SANDING SEALER**

Lenmar's DuraLaq™ 1C.201 is a ready-to-spray, nitrocellulose sanding sealer designed for interior wood applications only. The primary benefits of this sealer include its ease of application, ease of repair, and flow/leveling characteristics. When properly applied this product offers good initial build and excellent adhesion on properly prepared wood surfaces. This product sands easily and powders nicely to provide a smooth sealed foundation for follow-on coats. DuraLaq™ 1C.201 is compatible with any Lenmar nitrocellulose lacquer topcoat. It is not recommended for use over pickle finishes or white stains.

**ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 4 MILS DRY. LENMAR PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.**

**BENEFITS:**

- 20% SOLID CONTENT
- VOC & HAPS COMPLIANT
- SANDS EASILY
- COST SAVINGS
- FAST DRYING
- DESIGNED FOR EASY SPRAYING

**RECOMMENDED USES:**

- WINDOW & DOOR TRIM
- FINE FURNITURE
- HIGH END INTERIOR WOOD
- DOOR TRIM & CROWN MOLDING
- INTERIOR DOORS & HAND RAILS

**CHARACTERISTICS:**

Weight Per Gallon: 7.3 – 7.5 lbs.

% Weight Solids: 18 – 20

% Volume Solids: 13 – 14

Viscosity # 2 Zahn: 23 – 26 Sec.

VOC: Does not exceed 670 g/l  
or 5.5 lb./gal.

HAPS: < 0.8 lb. of HAPS per lb. of Solids

**DRY TIMES:**

Sand: 20 – 30 min.

Recoat: 30 min.

**CLEAN UP:** 1A.519 Lacquer Thinner

**RECOMMENDED SYSTEM:**

Over properly prepared interior wood surfaces, apply one coat of DuraLaq™ 1C.201, let dry, then sand. Topcoat with desired sheen level using any of the DuraLaq™ Series Lacquers. For additional resistance to moisture and chemicals, try the following Lenmar Finishing Systems: UltraUniLaq™ Acrylic 1M.97X series, UltraLaq™ Precat 1D.33X series, or MegaVar™ 1M.430X Series Do not apply more than two topcoats.

**ENTIRE SYSTEM SHOULD NOT EXCEED 4 MILS DRY.**

**SPECIFICATIONS:**

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Final sand wood with 120 to 150-grit sandpaper, depending on species, and remove all dust. Mix DuraLaq™ 1C.201 thoroughly and reduce as necessary with Lenmar's 1A.519 or 1A.406 lacquer thinners, to achieve proper atomization. Apply one coat at 3-4 wet mils, allow to dry, then sand with 280-320 grit silicon carbide sandpaper. Select the sheen required from any of the DuraLaq™ Series products, mix well and apply at least two coats. These products may be reduced with 1A.406 or 1A.519 or use 1A.114 retarder if necessary to prevent blushing. Check with equipment manufacturer for proper settings to achieve the optimum atomization. Do not thin inconsistent with local regulations. Read label and MSDS for additional information and warnings.

Jun 06

1C.201

**FOR MORE INFORMATION AND ORDERING, CALL TOLL FREE: 800 966-7020**

**Disclaimer:** These products are recommended for interior use only.

While all data given is believed to be accurate, it is presented as typical (as formulated) values and may not represent actual values.

Do not mix finishing systems. Insl-x Corp. will not be held responsible for failure resulting from the mixing of products or systems.

Due to variations in field conditions and procedures, Insl-x Corp. makes no warranty or guarantee as to the final results achieved.

Abnormal conditions of temperature and humidity may adversely affect product performance.

All products to be applied by spray only. Do not brush or roller these coatings. Apply a maximum of 4 dry mils.

User should determine the suitability of this product for the intended purposes, and assumes all risk and liability.