

1C.800**ULTRALAQ™ WHITE PRECATALYZED UNDERCOATER**

Lenmar's UltraLaq™ 1C.800 White precatalized undercoater is designed to serve as a comprehensive undercoater for use on cabinets and all fine wood finishing. The high solid content offers excellent adhesion and sands easily to provide an ideal foundation for the UltraLaq™ 1M.80X Series white precatalized topcoats. Additional benefits include ready-to-spray viscosity, fast drying properties, and chemical and moisture resistance. 1C.800 UltraLaq™ white precatalized undercoater is recommended over solid wood and MDF, and for use with all Lenmar Precatalyzed and Conversion Varnish finishes. If applied properly in conjunction with precatalized or catalyzed topcoats, the ensuing system passes the KCMA standards. This product is VOC and HAP compliant.

1C.800

ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 5 MILS DRY. LENMAR PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.

BENEFITS:

- EXCEEDS KCMA STANDARDS
- EXCELLENT PENETRATION
- HIGH HIDING
- READY TO SPRAY VISCOSITY
- RESISTS COLD CHECKING
- SANDS EASILY

RECOMMENDED USES:

- WINDOW AND DOOR TRIM
- FURNITURE
- KITCHEN CABINETS
- BATHROOM VANITIES
- DISPLAYS

CHARACTERISTICS:

Weight Per Gallon: 9.0 – 9.1 lbs.
 % Weight Solids: 41 – 43
 % Volume Solids: 23 – 25
 Viscosity # 2 Sig. Zahn: 17 – 27 Sec.
 VOC: Does not exceed 610 g/l
 or 5.1 lb./gal.
 HAPS: < 0.2lb. of HAPS per lb. of Solids
 DRY TIMES @ 3 – 4 mils wet
 Sand: 20 -30 min.
 Recoat: 30 - 60 min.

CLEAN UP: 1A.519 Lacquer Thinner

RECOMMENDED SYSTEM:

Over properly prepared interior wood surfaces, apply one full coat of 1C.800 White Precatalyzed undercoater, allow to dry, then sand. Select the desired sheen from the 1M.80X Series topcoats, shake well and apply by spray only in an even wet coat. Allow to dry 30 minutes then scuff sand and apply a final topcoat. Total system should be three coats, either 2 undercoats and one topcoat or one undercoat and two topcoats.

ENTIRE SYSTEM SHOULD NOT EXCEED 5 MILS DRY.

SPECIFICATIONS:

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Sand wood with no finer than 150-grit sandpaper and remove all dust. Mix all products thoroughly and apply finish by spray only. Check with equipment manufacturer for proper settings to achieve proper atomization. Apply one coat of UltraLaq™ 1C.800 White Precatalyzed Undercoater. Allow to dry, then sand with 280-320 grit, non-steared, silicon carbide sandpaper. Two coats may be necessary on MDF. Sand immediately prior to application of topcoats. Select topcoat from the UltraLaq™ 1M.80X series (or any other precatalized or post-catalyzed Lenmar system.) Apply two coats, allow to dry fully, then scuff sand between each. Product may be adjusted with 1A.114 retarder or 1A.406 thinner if required for specific conditions. Do not thin inconsistent with local regulations. Read label and MSDS for additional information and directions.

Jun 08

FOR MORE INFORMATION AND ORDERING, CALL TOLL FREE: 800 966-7020

Disclaimer: These products are recommended for interior use only. While all data given is believed to be accurate, it is presented as typical (as formulated) values and may not represent actual values. Do not mix finishing systems. Insl-x will not be held responsible for failure resulting from the mixing of products or systems. Due to variations in field conditions and procedures, Insl-x makes no warranty or guarantee as to the final results achieved. Abnormal conditions of temperature and humidity may adversely affect product performance. All products to be applied by spray only. Do not brush or roller these coatings. Apply a maximum of 5 dry mils. User should determine the suitability of this product for the intended purposes, and assumes all risk and liability.