

1LL.110 GLOSS	(90)
1LL.117 SEMI-GLOSS	(60)
1LL.114 SATIN	(40)
1LL.113 EGGSHELL	(25)

DURALAQ™ WATER WHITE N/C CLEAR LACQUER

Lenmar's DuraLac™ 1LL.11X Series, high performance, 20% solids, water white nitrocellulose lacquer is ideal for most interior wood surfaces that require the highest quality lacquer system. Its primary benefits include exceptional flow, leveling and spray characteristics, fast drying and VOC/HAPS compliant. The ready-to-spray viscosity saves time and insures job-to-job consistency and performance. Only the highest quality raw materials are uniquely blended into this lacquer which gives this water white topcoat its initial clarity. Once dry, this finish will resist cold checking for lasting durability. This lacquer is pre-mixed in four separate sheen levels. Not recommended for use over pickle stains, pastel or off-white finishes. For a true non-yellowing finish over these types of projects, try Lenmar's Ultra-UniLac™ 1M.97X CAB Acrylic Series.

ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 4 MILS DRY. LENMAR PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.

BENEFITS:

- EXCELLENT FLOW & LEVELING
- VOC & HAPS COMPLIANT
- READY TO SPRAY VISCOSITY
- RESISTS COLD CHECKING
- WATER WHITE CLARITY

RECOMMENDED USES:

- FINE FURNITURE
- WINDOW & DOOR TRIM
- BASEBOARDS & MOLDINGS
- INTERIOR DOORS & HAND RAILS
- OTHER INTERIOR WOOD FINISHING

CHARACTERISTICS:

Weight Per Gallon: 7.2 – 7.4 lbs.
 % Weight Solids: 19 – 21
 % Volume Solids: 13 – 15
 Viscosity # 2 Zahn EZ: 17 – 21 seconds
 VOC: Does not exceed 680 g/l
 or 5.7 lb./gal.
 HAPS: < 0.7 lb. of HAPS per lb. of Solids
 DRY TIMES @ 3 – 4 mils wet
 Sand: 15 – 20 min.
 Recoat: 30 min.

CLEAN UP: 1A.519 Lacquer Thinner

RECOMMENDED SYSTEM:

Over properly prepared wood surfaces apply one full coat of 1C.203, or other water white sealer, allow it to dry, then sand. Select the desired sheen from the DuraLac™ 1LL.11X Series topcoats, shake well and apply two even wet coats of 3-4 mils. Allow this to dry, scuff sanding between each coat. Do not exceed more than two topcoats. For additional resistance to moisture and chemicals, try the following Lenmar Finishing Systems: UltraUniLac™ Acrylic 1M.97X series, UltraLac™ Precat 1D.33X series, or MegaVar™ 1M.430X Series.

ENTIRE SYSTEM SHOULD NOT EXCEED 4 MILS DRY.

SPECIFICATIONS:

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Final Sand wood no finer than 120-150-grit sandpaper, depending upon the species, and remove all dust. Duralac™ 1LL.11X lacquers should be applied by spray only. Check with equipment manufacturer for proper settings to achieve good atomization. Select sanding sealer, and apply according to PDS/Label directions. Allow to dry, then sand with 320-grit, silicon carbide sandpaper prior to finish coating. Apply two coats of DuraLac™ 1LL-11X topcoats, allow to dry between coats, then scuff sand. Product is ready to spray, but small amounts of 1A.114 Lacquer Retarder may be necessary during adverse weather conditions. Do not thin inconsistent with local regulations. Read label and MSDS for additional information and warnings.

1LL.11X

Jun 06

FOR MORE INFORMATION AND ORDERING, CALL TOLL FREE: 800 966-7020

Disclaimer: These products are recommended for interior use only.

While all data given is believed to be accurate, it is presented as typical (as formulated) values and may not represent actual values. Do not mix finishing systems. Insl-x Corp. will not be held responsible for failure resulting from the mixing of products or systems. Due to variations in field conditions and procedures, Insl-x Corp. makes no warranty or guarantee as to the final results achieved. Abnormal conditions of temperature and humidity may adversely affect product performance. All products to be applied by spray only. Do not brush or roller these coatings. Apply a maximum of 4 dry mils. User should determine the suitability of this product for the intended purposes, and assumes all risk and liability.