

- 1M.979 GLOSS (85+)**
- 1M.976 SEMI-GLOSS (60)**
- 1M.974 SATIN (40)**
- 1M.972 DULL RUBBED (20)**

Ultra-UNILAQ™ CAB ACRYLIC TOPCOAT

The Ultra-UniLaq™ 1M.97X Series products are unique cellulose acrylic butyrate (CAB) lacquers designed for woodworkers who demand ultimate clarity found only in a true non-yellowing solvent-borne lacquer. 1M.97X Series products are unlike traditional nitrocellulose lacquers in appearance; they offer resistance to moisture, exceptional solids content, ready-to-spray viscosity and are HAPS/VOC compliant. These fast drying acrylic butyrate lacquers provide a durable finish that will resist cold checking and remain crystal clear over time. This product is ideal over pickle white stains, natural finishes or white systems.

ENTIRE SYSTEM SHOULD NOT EXCEED MORE THAN 4 MILS DRY. LENMAR PRODUCTS ARE DESIGNED FOR INTERIOR USE, BY SPRAY APPLICATION ONLY.

BENEFITS:

- NON-YELLOWING
- VOC & HAPS COMPLIANT
- READY TO SPRAY
- SELF SEALING
- RESISTS MOISTURE

RECOMMENDED USES:

- PICKLE WHITE STAIN
- CLEAR/WHITE KITCHEN CABINETS
- CLEAR/WHITE BATHROOM VANITIES
- CLEAR/WHITE DISPLAYS
- CLEAR/WHITE FIXTURES
- NATURAL/LIGHT STAIN FINISHES

CHARACTERISTICS:

Weight Per Gallon: 7.4 – 7.6 lbs.
 % Weight Solids: 23 – 25
 % Volume Solids: 18 – 20
 Viscosity # 2 Zahn: 24 – 28 seconds
 VOC: Does not exceed 680 g/l
 or 5.7 lb./gal.
 HAPS: < 0.61 lb. of HAPS Per lb. of Solids
 COLOR: Crystal Clear & Non-Yellowing
 DRY TIMES @ 3 -- 4 mils wet
 Sand: 25 -- 30 min.
 Recoat: 30 -- 45 min.

CLEAN UP: 1A.519 Lacquer Thinner

RECOMMENDED SYSTEM:

The Lenmar Ultra-UniLaq™ 1M.97X Series product should be used with the Ultra-UniLaq™ 1C.475 CAB Acrylic Sanding Sealer. Follow with two coats of the selected sheen from the 1M.97X Series. Sand between each coat and apply no more than 3-4 mils per coat.

ENTIRE SYSTEM SHOULD NOT EXCEED 4 MILS DRY.

SPECIFICATIONS:

Moisture content of wood should be no higher than 9%. Wood must be free of surface contaminants. Sand wood with no finer than 150-grit sandpaper and remove all dust. Mix all products thoroughly and apply finish by spray only. Check with equipment manufacturer for proper settings to achieve proper atomization. Apply UltraUniLaq™ 1C.475, CAB Acrylic Sanding Sealer as a first coat, let dry and sand with 280-320 grit, silicon carbide sandpaper. Follow with two additional wet coats (3-4 mils) of UltraUniLaq™ 1M.97X series topcoat in the desired sheen. Scuff sand with 280-320 grit sandpaper between all coats. Reduce only with 1A.406 thinner, or 1A.114 retarder. Use sparingly only as needed for specific application conditions or to obtain good atomization. Not designed for use with Quickstain glazes. Do not thin inconsistent with local regulations. Read label and MSDS for additional information and directions.

1M.97X

Jun 06

FOR MORE INFORMATION AND ORDERING, CALL TOLL FREE: 800 966-7020

Disclaimer: These products are recommended for interior use only. While all data given is believed to be accurate, it is presented as typical (as formulated) values and may not represent actual values. Do not mix finishing systems. Insl-x Corp. will not be held responsible for failure resulting from the mixing of products or systems. Due to variations in field conditions and procedures, Insl-x Corp. makes no warranty or guarantee as to the final results achieved. Abnormal conditions of temperature and humidity may adversely affect product performance. All products to be applied by spray only. Do not brush or roller these coatings. Apply a maximum of 4 dry mils. User should determine the suitability of this product for the intended purposes, and assumes all risk and liability.